

CAMPUS® Datasheet

PLEXIGLAS® Resist zk6BR - PMMA-I
Evonik Industries AG



Product Texts

Productprofil:

PLEXIGLAS® Resist zk6BR is an amorphous, impact-modified thermoplastic molding compound (PMMA-I).

Typical properties of impact-modified PLEXIGLAS® molding compounds are:

- high weather resistance
- excellent transmission and clarity
- brilliant appearance
- the pleasant feel and sound of the moldings.

PLEXIGLAS® Resist zk6BR is characterized by the following special properties:

- maximum break resistance and impact strength,
- improved resistance to stress cracking
- balanced property profile
- AMECA listing.

Application:

Used for extruding and coextruding sheets and profiles as well as for injection molding

Example:

extruded and injection-molded luminaire covers, extruded hollow profiles, writing utensils such as stencils and fountain pens, appliance housings, coextruded profiles for window frames, gutters, downspouts, and housewares such as cutlery handles, bowls, cookie jars.

Processing:

PLEXIGLAS® Resist zk6BR can be processed on machines with 3-zone general purpose screws for engineering thermoplastics.

Physical Form / Packaging:

PLEXIGLAS® Resist zk molding compounds are supplied as pellets of uniform size in 25kg polyethylene bags or in 500kg boxes with PE lining; other packaging on request.


Rheological properties	Value	Unit	Test Standard
Melt volume-flow rate, MVR	1.6	cm ³ /10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	3.8	kg	ISO 1133
Mechanical properties	Value	Unit	Test Standard
Tensile modulus	1800	MPa	ISO 527-1/-2
Yield stress	45	MPa	ISO 527-1/-2
Yield strain	5	%	ISO 527-1/-2
Nominal strain at break	>50	%	ISO 527-1/-2
Tensile creep modulus, 1h	1400	MPa	ISO 899-1
Tensile creep modulus, 1000h	900	MPa	ISO 899-1

PLEXIGLAS® Resist zk6BR - PMMA-I
Evonik Industries AG


Charpy impact strength, +23 °C	80	kJ/m²	ISO 179/1eU
Thermal properties	Value	Unit	Test Standard
Glass transition temperature, 10 °C/min	109	°C	ISO 11357-1/-2
Temp. of deflection under load, 1.80 MPa	88	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	93	°C	ISO 75-1/-2
Vicat softening temperature, 50 °C/h 50N	95	°C	ISO 306
Coeff. of linear therm. expansion, parallel	110	E-6/K	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested (1.5)	1.6	mm	IEC 60695-11-10
Yellow Card available	Yes	-	-
Oxygen index	17.5	%	ISO 4589-1/-2
Electrical properties	Value	Unit	Test Standard
Relative permittivity, 100Hz	3.7	-	IEC 60250
Relative permittivity, 1MHz	2.9	-	IEC 60250
Dissipation factor, 100Hz	500	E-4	IEC 60250
Dissipation factor, 1MHz	300	E-4	IEC 60250
Volume resistivity	>1E13	Ohm*m	IEC 60093
Surface resistivity	1E13	Ohm	IEC 60093
Comparative tracking index	600	-	IEC 60112
Other properties	Value	Unit	Test Standard
Water absorption	1.9	%	Sim. to ISO 62
Humidity absorption	0.5	%	Sim. to ISO 62
Density	1160	kg/m³	ISO 1183
Material specific properties	Value	Unit	Test Standard
Luminous transmittance	91	%	ISO 13468-1, -2
Rheological calculation properties	Value	Unit	Test Standard
Density of melt	1040	kg/m³	-
Thermal conductivity of melt	0.19	W/(m K)	-
Spec. heat capacity melt	2440	J/(kg K)	-
Eff. thermal diffusivity	7.49E-8	m²/s	-
Ejection temperature	75	°C	-
Test specimen production	Value	Unit	Test Standard
Injection Molding, melt temperature	255	°C	ISO 294
Injection Molding, mold temperature	50	°C	ISO 10724
Injection Molding, injection velocity	195	mm/s	ISO 294

Diagrams


Viscosity-shear rate




Shearstress-shear rate




Dynamic Shear modulus-temperature




Stress-strain




Secant modulus-strain




Stress-strain (isochronous) 23 °C




Creep modulus-time 23 °C




Specific volume-temperature (pvT)



Spec. enthalpy/mass-temp. (DSC)



Tensile modulus-temperature



Characteristics

Processing

Injection Molding, Film Extrusion, Profile Extrusion, Sheet Extrusion, Other Extrusion, Thermoforming

Delivery form

Pellets

Additives

Release agent

Special Characteristics

Light stabilized or stable to light, U.V. stabilized or stable to weather, Transparent

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information

Injection molding

PREPROCESSING

Predrying temperature: max. 85 °C

Predrying time in a desiccant-type drier: 2 - 3 h

PROCESSING

Melt temperature: 220 - 260 °C

Mold temperature: 50 - 70 °C

Profile extrusion

PREPROCESSING

Predrying temperature: max. 85 °C

Predrying time in a desiccant-type drier: 2 - 3 h

PROCESSING

Melt temperature: 220 - 260 °C

Die temperature: 220 - 260 °C

Sheet extrusion

PREPROCESSING

Predrying temperature: max. 85 °C

Predrying time in a desiccant-type drier: 2 - 3 h

PROCESSING

Melt temperature: 220 - 260 °C

Die temperature: 220 - 260 °C

Chemical Media Resistance

PLEXIGLAS® Resist zk6BR - PMMA-I
Evonik Industries AG

Acids

- ☹️ Citric Acid solution (10% by mass) (23 °C)
- ☹️ Lactic Acid (10% by mass) (23 °C)
- ☹️ Sulfuric Acid (38% by mass) (23 °C)
- ☹️ Sulfuric Acid (5% by mass) (23 °C)

Bases

- ☹️ Sodium Hydroxide solution (35% by mass) (23 °C)
- ☹️ Sodium Hydroxide solution (1% by mass) (23 °C)
- ☹️ Ammonium Hydroxide solution (10% by mass) (23 °C)

Hydrocarbons

- ☹️ n-Hexane (23 °C)

Standard Fuels

- ☹️ Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23 °C)
- ☹️ Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23 °C)
- ☹️ Diesel fuel (pref. ISO 1817 Liquid F) (23 °C)

Other

- ☹️ 50% Oleic acid + 50% Olive Oil (23 °C)
- ☹️ Water (23 °C)

All listed technical data are typical values intended for your guidance.
They are given without obligation and do not constitute a materials
specification. Should you have any further questions concerning material
behavior or properties, please contact us at the following address :

for PA: Evonik Resource Efficiency GmbH
RE-HP-IM-TAQ-PT
Gebäude 1227 / PB 16
D-45764 Marl
Phone: +49-(0)2365/49-2720
Fax: +49-(0)2365/49-2070
E-Mail: campusplastics@evonik.com

for PMMA: Evonik Performance Materials GmbH
Marketing / Campus
Kirschenallee
D-64293 Darmstadt
Germany
Phone: +49 - (0) 61 51 / 18-47 11
Fax: +49 - (0) 61 51 / 18-31 77
E-Mail: campusplastics@evonik.com

Internet: <http://www.plexiglas-polymers.com>

® = registered trademark

PLEXIGLAS® is a registered trademark of Evonik Röhm GmbH, Germany,
outside of the Americas. Within the Americas it is sold as ACRYLITE®,
which is a registered trademark of Evonik Cyro LLC, USA.
PLEXIMID® is a registered trademarks of Evonik Röhm GmbH, Germany.
CYROLITE® and XT® polymer are registered trademarks of Evonik Cyro LLC, USA.

PLEXIGLAS® Resist zk6BR - PMMA-I
Evonik Industries AG

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

NAFTA:

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

Sales range and technical data subject to alteration.